

Eurovent[®] STRONG

Eurosystem Polska Sp. z o.o.
 ul. Wiejska 13 46-055 Przywory, Poland
 NIP PL 9372516153
 REGON 240529246

e-mail: info@eurovent.pl
 www.eurovent.pl

Updated: 12/2007

technical data

CE

Eurovent[®] STRONG

Eurosystem Polska Sp. z o.o.
 ul. Wiejska 13 46-055 Przywory, Poland, NIP PL 9372516153

07

EN 13859-1

Breather waterproof roof membrane manufactured by lamination outer layers of spunbonded polypropylene, inner layer of polypropylene microporous film and reinforced polyethylene grid meets the specific requirements for use as supported or unsupported pitched roof construction for both applications, timber sarking or directly over thermal insulation with recommended overlap. This product does not contain any dangerous substances.

Length	EN 1848-2	50m (+/- 0,5m)
Width	EN 1848-2	1,5m (+/-0,015mm)
Thickness	EN 1848-2	0,7 mm(+/- 0,1mm)
Straightness	EN 1848-2	conforming
Mass per unit area	EN 1848-2	160g/m ² (-8+16g/m ²)
Roll size		1,5mx50mb=75m ²
Pallet		40 rolls
Tensile properties:		
- maximum tensile force	EN 12311-1, EN 13859-1	MD 380N/50mm(-38N/50mm) / CD 300N/50mm(30N/50mm)
- elongation	EN 12311-1, EN 13859-1	MD 50% (+/-20%) / CD 65% (-30+20%)
Tearing Resistance:	EN 12310-1, EN 13859-1/B	MD 340N (-34N) / CD 320N (-32N)
Resistance to water penetration	EN 1928	W1
Water vapour transmission properties	EN 12572/C	Sd=0,02m (+0,015m)
Resistance to penetration of air	EN 12114	0,018m ³ /m ² .h. 50Pa
Reaction to fire	EN 13501-1	E, bottomed with insulation compound

Artificial ageing by long term exposure to the combination of UV radiation and elevated temperature and heat (annexe C, E 13859-1)

Resistance to water penetration	W1
Change tensile strength	< 20%
Change elongation	< 50%



Marcin Świerta
 Commercial Director Central Europe

Przywory, 15.12.2007