

Eurovent[®] PUR

Eurosystem Polska Sp. z o.o.
ul. Wiejska 13 46-055 Przywory
NIP PL 9372516153
REGON 240529246

e-mail: info@eurovent.de
www.eurovent.de

technical data

Eurovent PUR

Eurosystem Polska Sp. z o.o.
ul. Wiejska 13 46-055 Przywory, NIP PL 9372516153

Carrier	PE foam
Adhesive	Acrylic dispersion
Thickness	3mm
Peel	26N/25mm
Temp. resistance	-40 do +100C
Tensile strenght	MD/CD 325kPa/220kPa
Elongation	MD/CD 125%/115%
Compression strenght at 50%	98kPa
Compression strenght at 20%	20% po 0.5h, 12% po 24h
Water absorption	<1%
Working temp.	-30 to +80C
Width	40mm
Lenght	30lm



Marcin Świerta
Prezes

Przywory, 1.12.2009